

**Q FLEX IS A SINGLE PACK, QUICK CURING URETHANE JOINT SEALANT THAT GIVES HIGH FLEXIBILITY AND IS RESISTANCE TO AGEING**

### PREPARATION-DIRECTIONS-APPLICATION

Surface must be structurally sound, clean, dry & free of foreign matter. Remove oil, grease, asphalt, tar, paint, rust, wax waterproofing & form release agents.

For friable surfaces or water

immersion Q/Seal should be used as a primer.

For best performance, depth of sealant should be one half the joint width. Minimum depth should be 1/4". Cure of sealant is dependant upon absorption of moisture from the atmosphere. Cure progresses faster under conditions of high relative humidity.

To apply, angle out nozzle to appropriate size and puncture inner seal. Remove metal cover from base of cartridge with a screwdriver and fit in cartridge gun.

Fill from bottom joint to prevent air pockets & voids. Sealant may be tooled with shaping tool moistened with water. Wipe off & leave joint concave. Clean equipment immediately after use with Q/Solve.



#### Joint Uses:

- Jointing Rubber & EVA Mats
- Roof & Gutter
- Expansion
- Construction
- Pre Cast Panels
- Silage Pits
- Effluent Tanks
- Slurry Pits

Colour	Grey/Black
100% Modulus	0-21 NM
Initial Cure	4-6 Hours
Full Cure	3-7 Days
Elongation At Break	500%
Packed In	320 & 600 CC
Chemical Resistance	Good to a wide range of acids, alkalis, salt etc
Coverage	28 lin ft per 6mm by 6mm joint
Flash Point	>100°C
Vapour Pressure @ 20°C	<100 mbar
Specific Gravity @ 20°C	1.42 g/cm <sup>3</sup>
Solubility in/Miscibility	Insoluble

**USE GLOVES & PROTECTIVE EQUIPMENT. IF SPLASHED IN EYES FLUSH WITH PLENTY OF WATER & SEEK MEDICAL ADVICE. IF INGESTED DO NOT INDUCE VOMITING. SEEK MEDICAL ADVICE.**

**Equine • Agricultural • Gym • Play**

**WWW.QUATTRO.ORG.UK**